

Braided Line Technical Specification

ULTREX 8		
Breaking Strain (LB)	Breaking Strain (KG)	Diam. (mm)
11	5.1	0.11
13	5.9	0.13
16	7.5	0.15
19	8.8	0.17
25	11.6	0.19
31	14.2	0.21
34	15.6	0.23
37	17.2	0.26
40	18.5	0.28
46	20.9	0.30
51	23.5	0.33
62	28.4	0.37
68	31.2	0.40
78	35.6	0.45
88	40.2	0.50

Braided Line Technical Specification

Smoothex 4			
Breaking Strain (LB)	Breaking Strain (KG)	DEN	Diam. (mm)
13	6.0	50	0.14
20	9.0	75	0.16
25	11.2	100	0.18
31	14.0	125	0.20
37	16.8	150	0.24
43	19.6	175	0.26
46	20.8	200	0.28
52	23.4	225	0.30
57	26.0	250	0.32
61	27.5	275	0.35
66	30.0	300	0.40
76	34.3	350	0.45
85	38.4	400	0.50

Braided Line Technical Specification

Smoothex 8			
Breaking Strain (LB)	Breaking Strain (KG)	DEN	Diam. (mm)
40	18.0	75	0.20
49	22.4	100	0.23
62	28.0	125	0.28
74	33.6	150	0.33
86	39.2	175	0.40
92	41.6	200	0.45
103	46.8	225	0.50
115	52.0	250	0.52
121	55.0	275	0.57
132	60.0	300	0.60
151	68.6	350	0.65
169	76.8	400	0.70
211	96.0	500	0.75
243	110.4	600	0.80

Braided Line Technical Specification

Purex 4			
Breaking Strain (LB)	Breaking Strain (KG)	DEN	Diam. (mm)
7	3.1	30	0.12
11	5.2	50	0.14
17	7.8	75	0.16
23	10.4	100	0.18
29	13.0	125	0.20
34	15.6	150	0.24
40	18.2	175	0.26
42	19.2	200	0.28
48	21.6	225	0.30
53	24.0	250	0.32
58	26.4	275	0.35
63	28.8	300	0.40
71	32.2	350	0.45
81	36.8	400	0.50
101	46.0	500	0.55
116	52.8	600	0.60

Braided Line Technical Specification

Purex 8			
Breaking Strain (LB)	Breaking Strain (KG)	DEN	Diam. (mm)
23	10.4	50	0.18
34	15.6	75	0.20
46	20.8	100	0.23
57	26.0	125	0.28
69	31.2	150	0.35
80	36.4	175	0.40
84	38.4	200	0.45
95	432.2	225	0.50
106	48.0	250	0.52
116	52.8	275	0.57
127	57.6	300	0.60
142	64.6	350	0.65
162	73.6	400	0.70
202	92.0	500	0.75
232	105.6	600	0.80
296	134.4	800	0.90

Braided Line Technical Specification

Helix			
Breaking Strain (LB)	Breaking Strain (KG)	DEN	Diam. (mm)
4.4	2.0	100	0.10
6.0	2.6	100	0.12
8.0	3.9	150	0.14
11.0	5.2	200	0.16
14.0	6.5	250	0.18
17.0	7.8	300	0.20
20.0	9.1	350	0.23
23.0	10.4	400	0.26
30.0	13.0	500	0.30
35.0	15.5	600	0.35

Braided Line Technical Specification

Anchron			
Breaking Strain (LB)	Breaking Strain (KG)	DEN	Diam. (mm)
18	8.0	100	0.18
22	10.0	125	0.20
26	12.0	150	0.24
31	14.0	175	0.26
35	16.0	200	0.28
40	18.0	225	0.30
44	20.0	250	0.32
48	22.0	275	0.35
53	24.0	300	0.40
62	28.0	350	0.45
70	32.0	400	0.50